













| VAT | | C.I.No. (Vat) | Dyeing depth (%o.w.f) | Fastness Properties | | | | | | | | Dyeing method |
|---------------------------|---|---------------|-----------------------|---------------------|----------------|-----|--------------|-----|---------|-----|-----|---------------|
| | | | | Light (Xenou) | Washing (95°C) | | Perspiration | | Rubbing | | | |
| | | | | | CH | CO | CH | CO | Dry | Wet | | |
| Yellow G 100% |  | Y-1 | 4.0 | 6-7 | 5 | 5 | 5 | 5 | 5 | 5 | 4-5 | 1N |
| Yellow GCN 100% |  | Y-2 | 4.0 | 4 | 4-5 | 4-5 | 4-5 | 4-5 | 4-5 | 4-5 | 4 | 1N |
| Yellow F3GC |  | Y-33 | 4.0 | 6-7 | 5 | - | 5 | - | - | - | - | 1W |
| Golden yellow RK 100% |  | 0-1 | 4.0 | 6-7 | 4-5 | 4 | 4-5 | 4-5 | 4 | 3 | 1W | |
| Golden orange 2RT 100% |  | 0-2 | 4.0 | 5-6 | 4-5 | 5 | 5 | 5 | 4-5 | 4 | 1W | |
| Brill. Orange 3RK 100% |  | 0-3 | 4.0 | 7 | 4-5 | 5 | 5 | 5 | 3-4 | 3 | SIR | |
| Brill. Orange GR 100% |  | 0-7 | 4.0 | 6 | 5 | 5 | 4-5 | 5 | 4-5 | 3-4 | 1N | |
| Gold Orange G 100% |  | 0-9 | 4.0 | 5-6 | 4-5 | 4-5 | 4 | 4-5 | 4-5 | 4 | 1N | |
| Yellow 3RT 100% |  | 0-11 | 4.0 | 7 | 5 | 5 | 4 | 4 | 4-5 | 4 | 1N | |
| Pink R 100% |  | R-1 | 4.0 | 6 | 4-5 | 5 | 4-5 | 4-5 | 4-5 | 4 | SIR | |
| Red FBB 100% |  | R-10 | 4.0 | 6-7 | 4 | 4 | 4-5 | - | 2-3 | 4 | 1W | |
| Scarlet GG 100% |  | R-14 | 4.0 | 7 | 4-5 | 5 | 4 | 4-5 | 4-5 | 3-4 | 1NA | |

| VAT | | C.I.No. (Vat) | Dyeing depth (%o.w.f) | Fastness Properties | | | | | | | | Dyeing method |
|---------------------------|---|---------------|-----------------------|---------------------|----------------|-----|--------------|-----|---------|-----|-----|---------------|
| | | | | Light (Xenou) | Washing (95°C) | | Perspiration | | Rubbing | | | |
| | | | | | CH | CO | CH | CO | Dry | Wet | | |
| Bordeaux RR 100% |  | R-15 | 4.0 | 6-7 | 4-5 | 4-5 | 4 | 5 | 4-5 | 3-4 | 1N | |
| Scarlet R 100% |  | R-29 | 4.0 | 6 | 4-5 | 5 | 4-5 | 5 | 3-4 | 2-3 | 1W | |
| Rea F3B 100% |  | R-31 | 4.0 | 6-7 | 5 | 5 | 4 | 4-5 | 4-5 | 3 | 1W | |
| RED BB |  | R-32 | 4.0 | 5 | 3-4 | 4-5 | 4-5 | - | 4 | 4 | 1W | |
| Red EFR 100% |  | R-54 | 4.0 | 6 | 2-3 | 3-4 | 3-4 | 4-5 | 4-5 | 3 | 1N | |
| Violet 2R 100% |  | V-1 | 4.0 | 6 | 4-5 | 4-5 | 4-5 | 5 | 4-5 | 4 | 1N | |
| Violet 3B 100% |  | V-9 | 4.0 | 5-6 | 4-5 | 5 | 4-5 | 5 | 4-5 | 4 | 1N | |
| Indigo (Granular) 100% |  | B-1 | 4.0 | 3-4 | 2 | 4 | - | - | 1-2 | 1 | SIR | |
| Blue RSN 100% |  | B-4 | 4.0 | 7-8 | 4-5 | 4-5 | 4-5 | 4-5 | 4 | 3-4 | 1N | |
| Blue BC 100% |  | B-6 | 4.0 | 7-8 | 4-5 | 5 | 4-5 | 5 | 4-5 | 4-5 | 1N | |
| Blue GCDN 100% |  | B-14 | 4.0 | 7-8 | 5 | 5 | 4-5 | 5 | 4-5 | 4 | 1N | |
| Navy RAN 100% |  | B-18 | 4.0 | 7 | 3-4 | 4-5 | 4 | - | 4 | 3 | 1N | |
| Blue BO 100% |  | B-20 | 4.0 | 7-8 | 3-4 | 4-5 | 4-5 | 4-5 | 4 | 3 | 1N | |

| VAT | | C.I.No. (Vat) | Dyeing depth (%o.w.f) | Fastness Properties | | | | | | | | Dyeing method |
|------------------------------|---|---------------|-----------------------|---------------------|----------------|-----|--------------|-----|---------|-----|----|---------------|
| | | | | Light (xenou) | Washing (95°C) | | Perspiration | | Rubbing | | | |
| | | | | | CH | CO | CH | CO | Dry | Wet | | |
| Sulphur Vat Blue GMX 100% |  | B-42 | 4.0 | 5 | 4-5 | 3-4 | 4-5 | 3-4 | 2-3 | 2-3 | 1N | |
| Sulphur Vat Blue RNX |  | B-43 | 4.0 | 6-7 | 4 | 4-5 | 4-5 | 3 | 1-2 | 1-2 | 1N | |
| Green FFB 100% |  | G-1 | 4.0 | 7-8 | 4-5 | 5 | 5 | 4-5 | 4 | 4 | 1N | |
| Olive Green B 100% |  | G-3 | 4.0 | 7-8 | 4-5 | 4-5 | 4-5 | 4-5 | 3 | 3 | 1N | |
| Khaki 2G 100% |  | G-8 | 4.0 | 7-8 | 5 | 5 | 4 | 4 | 2 | 2 | 1N | |
| Black BB 100% |  | G-9 | 4.0 | 8 | 4-5 | 4-5 | 5 | 4-5 | 3 | 3 | 1N | |
| Olive MW 100% |  | G-13 | 4.0 | 7-8 | 4-5 | 4-5 | - | - | - | - | 1N | |
| Brown BR 100% |  | Br-1 | 4.0 | 7 | 4-5 | 4-5 | 4-5 | 4-5 | 4 | 4 | 1W | |
| Brown R 100% |  | Br-3 | 4.0 | 7-8 | 5v | 5 | 4 | 4-5 | 4-5 | 4-5 | 1W | |
| Brown 2R 100% |  | Br-57 | 4.0 | 7-8 | 5 | 4 | 5 | 4 | 3-4 | 3-4 | 1N | |
| Brown G 100% |  | Br-68 | 4.0 | 7-8 | 4-5 | 5 | 4-5 | 4-5 | 4 | 4 | 1W | |
| Brown GG 100% |  | Br-72 | 4.0 | 7-8 | 5 | 5 | 5 | 4-5 | 4-5 | 4-5 | 1W | |
| Grey M 100% |  | Bk-8 | 4.0 | 7 | 3-4 | 4-5 | 4-5 | 5 | 4-5 | 3 | 1N | |

| VAT | | C.I.No. (Vat) | Fastness Properties | | | | | | | | | |
|------------------|---|---------------|-----------------------|-----|---------------|----------------|-----|--------------|-----|---------|------|---------------|
| | | | Dyeing depth (%o.w.f) | | Light (Xenou) | Washing (95°C) | | Perspiration | | Rubbing | | Dyeing method |
| | | | | | | CH | CO | CH | CO | Dry | Wet | |
| Black RB 100% |  | Bk-9 | 8.0 | 7-8 | 4-5 | 4-5 | 3-4 | 4-5 | 3-4 | 2 | SRII | |
| Grey 3B 100% |  | Bk-16 | 8.0 | 6-7 | 4 | 4-5 | 4 | - | 4 | 3-4 | 1N | |
| Olive T 100% |  | Bk-25 | 4.0 | 7-8 | 4-5 | 4-5 | 4-5 | 4-5 | 4-5 | 3-4 | 1N | |
| Olive R 100% |  | Bk-27 | 4.0 | 7 | 4-5 | 4-5 | 4-5 | 4-5 | 4-5 | 4 | 1W | |
| Grey BG 100% |  | Bk-29 | 6.0 | 6-7 | 4-5 | 4-5 | 4 | 5 | 4 | 3 | 1W | |
| Black DB 100% |  | Bk-38 | 6.0 | 6-7 | 3-4 | 4 | 3 | 4-5 | 3-4 | 2-3 | 1N | |

Nuestras cartas cuentan con colores referenciales.